

TEST REPORT NO:049808

Date:23 March 2010

PUGI RG SRL
VIA GARIBALDI 33/B
51037 MONTALE PISTOIA
ITALY

The following sample(s) was/were submitted and identified by/on behalf of the client as:

Retailer	Not Specified
Description of article	Red Stretch Fabric
Retailer style number	Unknown
Retailer Standard Number	Unknown
Order No./ Buyer	CONVERT
Fabric / Yarn Quality	100% PL FR Recycled
Date Sample(s) Received:	11 March 2010

Test

BS EN 1021-1 Ignition Source 0
 (Cigarette) Incl water soak
 BS EN 1021-2 Ignition Source 1
 (match) Incl water soak
 BS 5852 Annex E Water Soak
 BS5852 Ignition Source 5 (cribs)

Remarks

The fabric tested meets the required standard for those tests carried out.

From the full range of tests incorporated in this specification, we have carried out those requested by the customer.

Signature

 Manager

For and on behalf of
 SGS Leicester Ltd.

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only

Customer:	Pugi RG Srl
Test Report No:	049808

Test Request

The sample supplied is a woven fabric and has been tested to EN 1021-1-2:2006, Smouldering Cigarette and Match Ignition.

Fibre Identification:

Reputed Fibre Composition: 100% PL FR Recycled

Pre-Treatment:

The sample was cleansed using a water-soak procedure at 40°C ± 1°C as described in Annex D and lined dried.

Conditioning:

The sample was conditioned at ambient indoor conditions for a minimum of 72 hours followed by conditioning in a standard atmosphere having a temperature of 23°C ± 2°C and a relative humidity of 50% r.h. ± 5% for a minimum of 16 hours.

Comments on Test Results:

The fabric sample supplied meets the requirements of EN 1021-1-2:2006 Smouldering Cigarette and Match test.

Results:

'The following test results relate only to the ignitability if the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard if the materials in use.'

Cigarette Test

Pass criteria: ~ When two samples are tested no progressive smouldering or flaming is to be observed within 1 hour of placement of the cigarette. If the cigarette fails to smoulder to its complete length, the test is repeated in a new position not less than 50mm from the previous damage. No progressive smouldering is to be present in the final examination.

	Cigarette Ignition	
Specimen Number	1	2
Smouldering time of the Cigarette	19mins 16 secs	20mins 11 secs
Smouldering	N	N
Flaming	N	N
Smoking	N	N
After Glow	N	N
Cover Splitting	Y	Y
Final Examination	PASS	PASS

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only

Customer:	Pugi RG Srl
Test Report No:	049808

Extent of Damage: ~

Cigarette 1						
Fabric	Seat Length	20	Seat Width	69		
	Back length	18	Back Width	68		
Foam	Seat Width	67	Seat Depth	9		
	Back length	18	Back Width	65	Back Width	7

Cigarette 2						
Fabric	Seat Length	20	Seat Width	68		
	Back length	20	Back Width	67		
Foam	Seat Width	66	Seat Depth	8		
	Back length	19	Back Width	64	Back Width	8

Match Test: ~

Pass Criteria: ~ Disregard flaming or progressive smouldering which ceases within 120seconds of the removal of the burner tube. Disregard smoking and afterglow which ceases within 15minutes of the removal of the burner tube as per British Standards committee CCM/44. No progressive smouldering is to be present in the final examination.

Match Test						
Specimen Number	1	Time	2	Time	3	Time
Smouldering	N	-	N	-	N	-
Flaming	N	-	N	-	N	-
Smoking	Y	7SECS	Y	9SECS	Y	8SECS
Afterglow	N	-	N	-	N	-
Cover split	Y	-	Y	-	Y	-
Final Examination	PASS		PASS		PASS	

Please note that the fabric sample was tested over combustion modified foam with a density of 35kg per M³.

Key to results: ~

Y= Yes N=No N/A= Not Applicable

P=Pass F=Fail DNS= Did not smoulder

Note. All dimensions quoted are in mm.

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only

Customer:	Pugi RG Srl
Test Report No:	049808

Test Request

The sample supplied is a woven fabric and has been tested to BS 5852:2006 Clause 11 using Ignition Source 5.

Fibre Identification

Reputed Fibre Composition 100% PL FR Recycled

Pre-Treatment:

The sample supplied was water soaked and dry in accordance to BS 5852:2006 Annex E

Conditioning:

Before testing the sample was conditioned in a indoor ambient conditions for 72 hours and in a standard atmosphere having a temperature of 20°C ± 5°C and a relative humidity of 50% r.h ± 20% for a minimum of 16hours.

Comments on Test Results

The sample supplied meets the requirements of BS 5852:2006 Clause 11, NI/5.

Results

"The following test results relate only to the ignitability of combination of upholstery composites (BS 5852:2006 Clause 11) under the particular conditions of the test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use."

Ignition Source 5

Pass Criteria: ~ Disregard flaming which ceases within 10 minutes. Smoke, heat or glowing which ceases within 60 minutes of igniting the crib.

No smouldering is to be present in the final examination.

Specimen Number	1	Time	2	Time
Smoking	Y	5 mins 54 secs	Y	6 mins 23 secs
Smouldering	N	-	N	-
Flaming	Y	4 mins 58 secs	Y	4 mins 8 secs
Afterglow	N	-	N	-
Flame front reaches extremities within the test duration (other than the top of vertical part)	N	-	N	-
Mass Loss (Grams)	33g	-	32g	-
Cover Split	Y	-	Y	-
Final examination (ignition or Non-Ignition)	Non-Ignition		Non-Ignition	

Please note that the fabric sample was tested over combustion modified foam with a density of 35kg per M³.

Key: Y = Yes N = No N/A = Not Applicable
P = Pass F = Fail

End Of Report

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only