



Test report n° 033E/2014/LA

**MEASUREMENT OF SOUND ABSORPTION IN A REVERBERATION ROOM  
ACCORDING TO ISO 354 AND ISO 11654 STANDARDS**

**Manufacturer:** GABER S.r.l. Via Schiavonesca, 75/1 – 31030 Caselle di Altivole (TV) Italy.

**Test specimen:** panel mod. "STILLY".

**Applicant:** GABER S.r.l.

**Test specimen assemblers:** GABER S.r.l.

**Test date:** 11/03/2013.

**Test specimen description, mounting and position in the reverberation room:** see page 2.

| Freq.<br>f [Hz] | T <sub>1</sub> [s]<br>empty<br>room | T <sub>2</sub> [s]<br>room with<br>test<br>specimen | A [m <sup>2</sup> ]<br>(*) | α <sub>s</sub> [%]<br>(**) |
|-----------------|-------------------------------------|-----------------------------------------------------|----------------------------|----------------------------|
| 100             | 19,37                               | 15,04                                               | 0,52                       | 0,05                       |
| 125             | 20,39                               | 13,74                                               | 0,82                       | 0,08                       |
| 160             | 16,45                               | 9,77                                                | 1,43                       | 0,13                       |
| 200             | 16,35                               | 8,03                                                | 2,18                       | 0,20                       |
| 250             | 16,27                               | 6,52                                                | 3,15                       | 0,29                       |
| 315             | 15,08                               | 5,27                                                | 4,22                       | 0,39                       |
| 400             | 13,89                               | 4,12                                                | 5,83                       | 0,54                       |
| 500             | 12,48                               | 3,52                                                | 6,96                       | 0,64                       |
| 630             | 11,62                               | 3,01                                                | 8,41                       | 0,78                       |
| 800             | 10,52                               | 2,83                                                | 8,86                       | 0,82                       |
| 1000            | 8,91                                | 2,64                                                | 9,16                       | 0,84                       |
| 1250            | 7,72                                | 2,74                                                | 8,19                       | 0,76                       |
| 1600            | 6,81                                | 2,78                                                | 7,50                       | 0,69                       |
| 2000            | 5,55                                | 2,65                                                | 7,14                       | 0,66                       |
| 2500            | 4,49                                | 2,48                                                | 6,77                       | 0,62                       |
| 3150            | 3,59                                | 2,24                                                | 6,77                       | 0,62                       |
| 4000            | 2,69                                | 1,88                                                | 6,95                       | 0,64                       |
| 5000            | 1,85                                | 1,46                                                | 7,30                       | 0,67                       |

Note:

(\*) The equivalent sound absorption area of the test specimen, A, has been calculated using the formula:


$$A = 55,3 \frac{V}{c} \left( \frac{1}{T_2} - \frac{1}{T_1} \right) - 4V(m_2 - m_1) \quad [\text{m}^2]$$

where: V [m<sup>3</sup>] is the volume of the empty reverberation room;  
c [m/s] is the propagation speed of the sound in air;  
T<sub>1</sub> [s] is the reverberation time of the empty reverberation room;  
T<sub>2</sub> [s] is the reverberation time of the reverberation room after the test specimen has been introduced;  
m<sub>1</sub> [m<sup>-1</sup>] is the power attenuation coefficient of the empty reverberation room calculated according to ISO 9813-1;  
m<sub>2</sub> [m<sup>-1</sup>] is the power attenuation coefficient of the reverberation room calculated according to ISO 9813-1.

(\*\*) The sound absorption coefficient α<sub>s</sub> [%], Has been calculate using the formula

$$\alpha_s = \frac{A}{S} \quad [\%]$$

where: A [m<sup>2</sup>] is the equivalent sound absorption area of the test specimen;  
S [m<sup>2</sup>] is the area covered by the test specimen.



Head of the Laboratory

*[Signature]*

This test report consists of two pages. Its partial reproduction is allowed only under written permission of this Department.

Padova, 17/03/2014

page 1 of 2.

**Weighted sound absorption coefficient (ISO 11654):**

- $\alpha_w = 0,60$
- Sound absorption class: C

**Test specimen set-up:** according to ISO 354 standard. Perimeter edges of the test specimen covered with an acoustically reflective frame made of MDF, 20 mm thick.



**Test specimen description:** panel mod. "STILLY" (nominal size 440 mm x 440 mm; maximum height 40 mm; mass 0,4 kg) composed of a plastic support frame and polyester felt (6 mm thick) lined with Trevira polyester tissue.

**Test conditions:**

|                                                    |                       |
|----------------------------------------------------|-----------------------|
| Area of test specimen:                             | 10,842 m <sup>2</sup> |
| Average air temperature in reverberant room:       | 17 °C                 |
| Average air relative humidity in reverberant room: | 43 %                  |
| Atmospheric pressure:                              | 101,3 kPa             |

**Test room:** reverberant room of Department of Industrial Engineering, University of Padova; volume 211,2 m<sup>3</sup>; surface 214,38 m<sup>2</sup>.

**Measuring apparatus:** Notebook IBM T30, audio device DIGIGRAM VXpocket2, software Brüel & Kjær 7841 DIRAC, microphone G.R.A.S. type 40AQ (S/N 41471), preamplifier G.R.A.S. type 26CA (S/N 57851), signal conditioning amplifier 01dB OPUS (S/N 20225), power amplifier Brüel & Kjær 2716, omnidirectional sound source Brüel & Kjær 4295.

**Test procedure:** 4 microphone position and 4 source position in reverberant room, with 2 samplings for each combination of microphone and source position.

**Note:** measurements results in this test report are referred to the measured test specimen; there are no deviations from declared test methods.

\*\*\*

